



SUPERTHERM[®] TECHNICAL DATA SHEET

(06/9/06)

DESCRIPTION:

SUPER THERM is a unique one-part coating composed of high-performance aliphatic urethanes, elastomeric acrylics, and resin additives in a water-borne formula. SUPER THERM utilizes four different ceramics that block 95% of the sun's radiant heat - visual light, ultra violet rays and infrared rays. SUPER THERM is a permanently flexible "breathing" membrane that stops water penetration, and prevents corrosion and surface deterioration.

TYPICAL USES:

- * As a one-coat insulation system on exterior and interior substrates (roofs, walls, and floors)
- * As an insulator for transportation vehicles, refrigerated containers, and railroad cars
- * As insulation and to stop condensation on HVAC systems, tanks, and storage systems
- * As a one-coat "flexible and breathable" protective system over metal, concrete, masonry, and wood to stop water penetration and corrosion, resist dirt, mold, mildew, and pollution, increase longevity, and reduce surface maintenance
- * As a topcoat over RUST GRIP on metal roofs, or as an intermediate coat on flat roofs

APPLICATION METHODS:

SUPER THERM can be applied to metal, concrete, masonry, and wood. The application can be by spray, brush, or roller. For specific instructions on surface preparation, mixing, and application, please refer to the SPI's application instructions for SUPER THERM.

PHYSICAL DATA:

- * Solids: By weight 63.6% / By volume 68%.
- * Film Thickness: On all substrates SUPER THERM should be applied at 16 mils wet / 10 mils dry. Under no circumstances should SUPER THERM be applied at less than 10 mils dry.
- * Dry Time: One hour to touch at 70F. degrees and bright sun / Overcoat window is twohours or longer at 70F. degrees / Fully cures in twenty one days.
- * Lead and chromate free.
- * Cures by evaporation with no co-solvents present.
- * Weight: 11.88 lbs. per gallon.
- * Shelf Life: up to 3 years (unopened) under appropriate storage conditions (see MSDS).
- * VOC Level: 21 grams/liter.
- * pH: 8.5 - 9.0. * Viscosity: 105-110 KU.

TESTS AND CERTIFICATIONS:

- 1) USDA approved
- 2) Marine approvals for salt water/maritime use:
*DNV (Det Norske Veritas) *US Coast Guard

- *ABS (American Bureau of Shipping)
- *IMO (International Maritime Organization)
- 3) Energy Star Rating - approved and accepted as an energy partner for energy savings
- 4) Factory Mutual approval
- 5) ICC-ES Legacy Approval
- 6) UL (Underwriters Laboratory) approved
- 7) Cool Roof Rating Council approved and listed
- 8) Flame Spread Test (ASTM E8489/UL 723):
Flame = 0 / Smoke = 0 / Class A Flame Spread
- 9) Flexibility (ASTM E1737): 180F deg. bend-passed
- 10) Adhesion (ASTM B3359): rated a 5B
- 11) Perm Rating (ASTM E96): 8.8 avg
- 12) Tensile Properties (ASTM D412): 444 psi
- 13) Abrasion Resistance (ASTM D4060): 3,000 cycles
- 14) Resistance to Salt Spray: 2000 hrs
- 15) Resistance to Wind Driven Rain (ASTM E514)
- 16) Sound Reduction: STC-Rated 48-51
- 17) RE20: two coats interior (BTU Test)
- 18) RE19: one coat exterior (ASTM C236)
- 19) Blocks 99.5% of infrared / 68% sound blockage
- 20) Resists mold and mildew
- 21) Blocks moisture in concrete blocks

SAFETY PRECAUTIONS:

Do not use this product without first taking all appropriate safety measures to prevent property damage and injuries. These measures may include, without limitation: proper ventilation, use of proper lamps, wearing of protective clothing and masks, tenting, and proper separation of application areas.

KEEP OUT OF REACH OF CHILDREN.

For more specific safety procedures, please refer to the SUPER THERM Material Safety Data Sheet.

LIMITATION OF LIABILITY: The information contained in this data sheet is based upon tests that we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the products made by SPI, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge is reliable. The products and information are designed for users having the requisite knowledge and industrial skills, and the end-user has the responsibility to determine the suitability of the product for its intended use.

SPI has no control over either the quality of condition of the substrate, or the many factors affecting the use and application of the product. Therefore, SPI does not accept any liability arising from loss, injury, or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The information contained in this data sheet is subject to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and the user has the responsibility to ensure that this sheet is current prior to using the product.